

April 1, 2016

**OPEN-GRADED FRICTION COURSE**

**Subsection 409.2.4, Composition of Mixture**, of the Standard Specifications: Replace the table with the following table and add the sentences about tolerances.

<b>Sieve Designation</b>	<b>% Passing</b>
¾ inch	100
½ inch	85.0 - 100.0
⅜ inch	55.0 - 75.0
No. 4	15.0 - 30.0
No. 8	5.0 - 15.0
No. 200	0.0 4.00
Range for % Binder	5.50 – 7.00

Design and set target mix design gradations within the master range above. Field tolerances are not permitted to extend outside of the ranges for each designated sieve.